

US009636485B2

(12) United States Patent

Simpson et al.

(54) METHODS FOR COUNTERACTING REBOUNDING EFFECTS DURING SOLID STATE RESISTANCE WELDING OF DISSIMILAR MATERIALS

(71) Applicant: Abbott Cardiovascular Systems, Inc.,

Santa Clara, CA (US)

(72) Inventors: John A. Simpson, Carlsbad, CA (US);

Jeffrey F. Dooley, Oceanside, CA (US); Matthew J. Gillick, Murrieta, CA (US)

(73) Assignee: Abbott Cardiovascular Systems, Inc.,

Santa Clara, CA (US)

(*) Notice: Subject to any disclaimer, the term of this

patent is extended or adjusted under 35

U.S.C. 154(b) by 181 days.

(21) Appl. No.: 13/744,276

(22) Filed: Jan. 17, 2013

(65) Prior Publication Data

US 2014/0200555 A1 Jul. 17, 2014

(51) **Int. Cl.**

B23K 9/00 (2006.01) **B23K 11/00** (2006.01)


(Continued)

(52) U.S. Cl.

(Continued)

(58) Field of Classification Search

CPC B23K 11/20; B23K 11/18; B23K 11/34; B23K 11/11; B23K 11/185; B23K 11/04; (Continued)



(10) Patent No.:

US 9,636,485 B2

(45) Date of Patent:

(56)

May 2, 2017

References Cited

U.S. PATENT DOCUMENTS

FOREIGN PATENT DOCUMENTS

CN 1846803 11/2010 EP 1388350 2/2004 (Continued)

OTHER PUBLICATIONS

Zapp Precision Wire Alloy MP35N (UNS R30035) Wire, Zapp Precision Wire, Inc., Accessed Feb. 21, 2014, pp. 1-4, Summerville, South Carolina.

(Continued)

Primary Examiner — David Angwin Assistant Examiner — Gyounghyun Bae (74) Attorney, Agent, or Firm — Workman Nydegger; John Kwok

(57) ABSTRACT

The present disclosure is directed to methods for joining initially separate members of different metallic materials, e.g., as in joining segments of a multi-segment intravascular guide wire, as well as multi-segment intravascular guide wires so formed. Initially separate members are provided, which members comprise different metallic materials relative to one another (e.g., stainless steel and nitinol). The members are aligned with one another, and a first force is applied to the members while delivering electrical current through the members to solid state weld the separate members to one another. A follow up force that is greater than the first force is applied as solid-state deformation occurs and a weld nugget forms between the members. The weld nugget so formed is thinner and of a larger transverse crosssectional area than would be produced without application of the follow up force.

23 Claims, 19 Drawing Sheets

